


Methacryl isoOctyl POSS®

Clear, low viscosity liquid.



HC0710.13

APPLICATIONS

Surface energy control, Interfacial compatibilization. Additionally dispersion enhancement and hydrophobicity can be realized in certain formulations.

TYPICAL PROPERTIES

Appearance	Clear low viscosity liquid
HC0710.13 Viscosity (@25 °C)	1348-1378 mPa s
Refractive Index	1.461@ 19.1 °C
HC0710.13 Formula Weight	1350.34 for octamer
Solvent Solubility	Cyclohexane, alcohols, ketones
Solvent Insolubility	Water

REGULATORY STATUS

R&D use only at this time.
Not a primary dermal irritant.

HANDLING PRECAUTIONS

Product safety information required for safe use is not included in this document. Before handling, read product and material safety data sheets and container labels for safe use, physical health and hazard information. For material safety data information, contact Hybrid.



BENEFITS

UV free radical and addition cure. The combination of reactivity provides for compatibilization, interfacial control and dispersion. The crosslinking capability in combination with isooctyl provides for hydrophobicity and reduced surface energy.

DESCRIPTION

Methacryl isooctyl POSS® is a hybrid molecule with an inorganic silsesquioxane core and organic reactive groups attached at the corners of the cage. Methacryl isooctyl POSS® is a molecular union of both functional chemistry and inorganic-organic compositions.

COMPATIBILITY

Methacryl isooctyl POSS® is provided in neat form and as a concentrate in solvents/monomers and resins.

Methacryl isooctyl POSS® is intended to be utilized as an additive. At low additive concentrations compatibility is expected with a wide range of resins and monomers bearing similar chemical functionality.

Compatibility testing is recommended for higher concentrations. Additional information and screening may be provided by Hybrid upon request.

ADDITIONAL DETAILS

Methacryl isooctyl POSS® is a mixture of cage sizes 8, 10, 12. The organic groups are randomly distributed around each cage core. ***The ratio of methacryl and isooctyl groups in the 13 product is approximately 2:6 for an octameric cage.***

The distribution of cage size, and functionality around the cage core is analogous to that for functional polymers.

Heteroleptic cage POSS are represented by the catalog designation HC. The structure shown is idealized and should not be considered exact.